

■ High-Entropy Alloys and Refractory Metals & Alloys

High-Entropy Alloys and Refractory Metals & Alloys		
Type	Product	Particle Size (µm)
Refractory Metal & Alloy Spherical Powder	Niobium C-103 (Nb-10Hf-1Ti) Alloy Powder	0-25, 15-53, 45-105
	Tungsten Rhenium (W-25Re) Alloy Powder	0-25, 15-53, 45-105
	Tantalum Tungsten (Ta10W) Alloy Powder	0-25, 15-53, 45-105
	Tantalum Tungsten (Ta7.5W) Alloy Powder	0-25, 15-53, 45-105
	Tantalum Tungsten (Ta2.5W) Alloy Powder	0-25, 15-53, 45-105
	Tungsten (W) Powder	0-25, 15-53, 45-105
	Molybdenum (Mo) Powder	0-25, 15-53, 45-105
	Tantalum (Ta) Powder	0-25, 15-53, 45-105
	Niobium (Nb) Powder	0-25, 15-53, 45-105
	Titanium (Ti) Powder	0-25, 15-53, 45-105
	Zirconium (Zr) Powder	0-25, 15-53, 45-105
	Hafnium (Hf) Powder	0-25, 15-53, 45-105
	Chromium (Cr) Powder	0-25, 15-53, 45-105
	Vanadium (V) Powder	0-25, 15-53, 45-105
High-Entropy Alloy (HEA) Spherical Powder	FeCoNiCrMn High-Entropy Alloy Powder	0-25, 15-53, 45-105
	FeCoNiCrAl High-Entropy Alloy Powder	0-25, 15-53, 45-105
	FeCoNiCrTi High-Entropy Alloy Powder	0-25, 15-53, 45-105
	FeCuNiCrAl High-Entropy Alloy Powder	0-25, 15-53, 45-105
	FeAlNiCrX High-Entropy Alloy Powder	0-25, 15-53, 45-105
	FeNiCoCr High-Entropy Alloy Powder	0-25, 15-53, 45-105
	CoCrNi High-Entropy Alloy Powder	0-25, 15-53, 45-105
	CoCrW High-Entropy Alloy Powder	0-25, 15-53, 45-105
	CoCrMo High-Entropy Alloy Powder	0-25, 15-53, 45-105
	CoFeNi High-Entropy Alloy Powder	0-25, 15-53, 45-105

■ Standard Metal Alloys and Thermal Spray Ceramics

Standard Metal Alloys and Thermal Spray Ceramics			
Type	Product		Particle Size (µm)
Standard Alloy Spherical Powder	Aluminum Alloy	AlSi, AlSiMg, 2024, 6061, 2A12	0-25, 15-53, 45-105
	Copper Alloy	CuSn, CuIn, CuZr, CuZn, CuAl	0-25, 15-53, 45-105
	Cobalt Alloy	CoCr, Haynes 188, Co6/12/21, Hipercor	0-25, 15-53, 45-105
	Iron Alloy	SS 17-4PH, SS 304, SS 316L, SS 420, Incoloy A286, Invar 36, Kovar	0-25, 15-53, 45-105
	Nickel Alloy	Inconel 625, 718, Hastelloy X, Nitinol, Haynes 230, Monel K-500, C276	0-25, 15-53, 45-105
	Titanium Alloy	TC4 (Ti-6Al-4V), TA19 (Ti-6Al-2Sn-4Zr-2Mo), TC11 (Ti-6.5Al-3.5Mo-1.5Zr-0.3Si), TA17, Ti-10V-2Fe-3Al, Ti-6Al-6V-2Sn	0-25, 15-53, 45-105
Thermal Spray Spherical Powder	Hafnium Carbide (HfC) Powder		0-25, 15-53, 45-105
	Hafnium Diboride (HfB2) Powder		0-25, 15-53, 45-105
	Hafnium Nitride (HfN) Powder		0-25, 15-53, 45-105
	Molybdenum Disilicide (MoSi2) Powder		0-25, 15-53, 45-105
	Niobium Carbide (NbC) Powder		0-25, 15-53, 45-105
	Tantalum Carbide (TaC) Powder		0-25, 15-53, 45-105
	Titanium Carbide (TiC) Powder		0-25, 15-53, 45-105
	Titanium Diboride (TiB2) Powder		0-25, 15-53, 45-105
	Tungsten Carbide (WC) Powder		0-25, 15-53, 45-105
	Vanadium Carbide (VC) Powder		0-25, 15-53, 45-105
	Zirconium Nitride (ZrN) Powder		0-25, 15-53, 45-105
	Zirconium Carbide (ZrC) Powder		0-25, 15-53, 45-105
	Zirconium Diboride (ZrB2) Powder		0-25, 15-53, 45-105